

测试报告

No. CANEC1204495202

日期: 2012年04月24日 第1页,共3页

汛龙实业有限公司

香港新界葵涌健康街1-7号致华工业大厦13字楼B室

以下测试之样品是由申请者所提供及确认: 光面/镜面/压花纹-流延聚丙烯薄膜

SGS工作编号: CP12-017253 - SZ
制造商: 东莞港龙彩印有限公司
目的地/国: 美国
原产国: 中国
样品接收日期: 2012年04月18日
测试周期: 2012年04月18日 - 2012年04月24日
测试要求: 根据客户要求测试
测试方法: 请参见下一页
测试结果: 请参见下一页

测试结果概要:

测试要求	结论
FDA 21 CFR 177.1520—最大可萃取量	合格
FDA 21 CFR 177.1520—密度 (23°C)	合格

结论: 应客户要求, 测试项目符合美国食品与药品管理局(FDA)法规的要求。

通标标准技术服务有限公司

授权签名

Alpher Qiu 丘尽花

批准签署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its preparation only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated, the results shown in this test report refer only to the sample(s) tested.

测试报告

No. CANEC1204495202

日期: 2012年04月24日 第2页,共3页

测试结果:

测试样品描述:

样品编号	SGS样品ID	描述
1	CAN12-044952.001	透明薄膜

FDA 21 CFR 177.1520—最大可萃取量

测试要求: 应客户要求, 根据美国FDA法规要求, 测定与食品接触而不用于烹饪中包装或盛放食品的烯烃共聚物的最大可萃取量。

测试方法: 参考US FDA 21 CFR 177.1520 d(3)(ii) & d(4)(ii)。

常用模拟液	时间	温度	最大允许限值	样品001	评论
正己烷	2hr	50°C	5.5% (w/w)	2.0% (w/w)	PASS
二甲苯	2hr	25°C	30% (w/w)	5.2% (w/w)	PASS

备注:

%w/w = 质量百分比

FDA 21 CFR 177.1520—密度 (23°C)

测试要求: 应客户要求, 根据美国FDA法规要求, 测定与食品接触而不用于烹饪中包装或盛放食品的烯烃共聚物的密度。

测试方法: 参考US FDA 21 CFR 177.1520 d(1)或ASTM D792:2008。

测试项目	限值	001
密度 (23°C), g/cm ³	0.850-1.000	0.888
评论		PASS

备注:本报告内容是参照报告编号为CANEC1204495201的中文译本, 中英文版本如有歧异, 概以英文版为准。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its preparation only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated, the results shown in this test report refer only to the sample(s) tested.

